



Chemline Z-8685-8686

Polyurethane Compound

Description

Chemline Z-8685-8686 is a clear, rigid, light and weather stable polyurethane compound.

Processing

Chemline Z-8685-8686 should be mixed thoroughly by a static mixer, or by hand, with a clean spatula in a clean disposable container such as a polypropylene beaker or plastic lined hot drink cup.

Storage

Both materials must be protected from moisture. Storage temperatures should be ambient. In storage, containers should be tightly closed since this material is moisture sensitive. Material should be warmed to 90-110°F prior to use. With proper storage practices, the shelf life of **Chemline Z-8685-5686** is 1 year in sealed bags and 90 days in disposable bags.

Safety

Chemline Z-8685-8686 is for industrial use only. Avoid contact with eyes and skin. Do not inhale or ingest. Be sure to read SDS in its entirety prior to use.

Properties of Components

Property	Clear Polyol	Aliphatic Iso
Mixing Ratio (by volume)	1	1
Mixing Ratio (by weight)	1	1
Specific Gravity	1.07	1.10
Density lbs/gal	8.9	8.74
Viscosity @ 100 °F	465 ± 50 cps	450 ± 200 cps
NCO Value	-	24.5% ± 0.5
Acid Value	Less than 0.75	-
Hydroxyl Value	315-325	-
Gel Time	4-7 minutes	
Cure Time	100-200°F (4-16 hours)	

Cured Elastomer Properties

Property	Value
Hardness, D-2240	Shore D 65-80
Heat Aging	7 days at 185°F, no change
Humidity Resistance	7 days 100% RH @ 200°F, no change
Shrinkage on Cure	0.5% cured at RT 1% cured @ 167°F

Revised 8/2020

Chemline, Inc. • 5151 Natural Bridge Rd. • St. Louis, MO 63115 • Phone: (314) 664 - 2230

• 19500 S. Alameda St. • Los Angeles, CA 90221 • Phone: (310) 764 - 0820

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by Chemline, Inc. hereunder are provided gratis and Chemline assumes no obligation or liability for the descriptions, designs, data and information given or results obtained, all such being given and accepted at your risk.