



Chemline 3795

Aliphatic Polyurea Spray Coating

Description

Chemline 3795 is a 1:1, fast-set, spray applied two-component aliphatic polyurea. When cured, it is highlighted by:

- √ Extremely high Color Stability and Gloss Retention, even with light or pastel colors
- √ Excellent adhesion to steel (with Chemprime 3550) and concrete (with Chemprime 3558)
- √ Zero VOCs and 100% solids

Application Recommendations

Chemline 3795 adheres to metal or concrete surfaces used over an appropriate primer. It should be applied through a two-component, heated, high pressure proportioning unit (1A:1B) capable of dynamic spray pressures of 2000-2400 psi.

For further detail consult the **Chemline 3795** Material Standard and seek a Chemline Technical Representative for equipment and application training.

Packaging, Storage & Shelf Life

Chemline 3795 is available in 55 gallon drums and 275 gallon totes. It should be stored in sealed containers between 60°F and 90°F. Shelf life is 12 months under normal conditions.

Safety

Chemline 3795 is for industrial use only. Avoid contact with eyes and skin. Do not inhale or ingest. When spraying, wear a respirator or fresh air hood. Spraying indoors requires forced ventilation. Be sure to read MSDS in its entirety prior to use.

Application Properties

Property	Value
Gel time	30 seconds
Tack free time	45 seconds
Recoat window	2 hours

Physical Properties

Property	Value
Hardness, Shore A, D-2240	95 A
Tensile strength, D-412	2200 psi
Tear strength, D-624	350 pli
Elongation, D-412	400 %

*Values obtained in laboratory setting for comparison purposes only and should not be considered specifications.

Revised 06/2017

Chemline, Inc. • 5151 Natural Bridge Rd. • St. Louis, MO 63115 • Phone: (314) 664 - 2230

• 19500 S. Alameda St. • Los Angeles, CA 90221 • Phone: (310) 764 - 0820

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by Chemline, Inc. hereunder are provided gratis and Chemline assumes no obligation or liability for the descriptions, designs, data and information given or results obtained, all such being given and accepted at your risk.