



Chemline 6080

Polyurea Lining for Secondary Containment Applications

Description

Chemline 6080 is a 1:1, fast-set, spray applied two-component polyurea coating. It is 100% solids and contains zero VOCs. When cured, it is highlighted by:

- √ Excellent resistance against chemicals used in the Oil and Gas Industry
- √ Extremely flexible and high elongation to conform to the substrate during movement
- √ Specifically designed to wet out geotextiles to create a tough, durable liner
- √ Fast setting to minimize down times of application areas

Application Recommendations

Chemline 6080 adheres extremely well to geotextile fabric. Typical applications include chemical containment and spill control, fuel loading and unloading stations and landfills.

Chemline 6080 should be applied through a two component, heated, high pressure proportioning unit (1A:1B) capable of dynamic spray pressures of 2000-2400 psi.

For further detail consult a Chemline Technical Representative for application training.

Packaging, Storage & Shelf Life

Chemline 6080 is available in 55 gallon drums and 275 gallon totes. It should be stored in sealed containers between 60°F and 90°F. Shelf life is 12 months under normal conditions.

Safety

Chemline 6080 is for industrial use only. Avoid contact with eyes and skin. Do not inhale or ingest. When spraying, wear a respirator or fresh air hood. Spraying indoors requires forced ventilation. Be sure to read MSDS in its entirety prior to use.

Application Properties

Property	Value
Application Temp	0°F to 110°F
Gel time	13 seconds
Tack free time	20 seconds

Physical Properties

Property	Value
Hardness, Shore A / D, D-2240	90 A / 40 D
Tensile strength, D-412	3300 psi
Tear strength, D-624	320 pli
Elongation, D-412	490 %

*Values obtained in laboratory setting for comparison purposes only and should not be considered specifications.

Revised 08/2017

Chemline, Inc. • 5151 Natural Bridge Rd. • St. Louis, MO 63115 • Phone: (314) 664 - 2230

• 19500 S. Alameda St. • Los Angeles, CA 90221 • Phone: (310) 764 - 0820

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by Chemline, Inc. hereunder are provided gratis and Chemline assumes no obligation or liability for the descriptions, designs, data and information given or results obtained, all such being given and accepted at your risk.