



# Chemline ARC-F

Aromatic Polyurea Coating

USGBC LEED, EQ Credit 4:

Low-emitting VOC Compliant Materials

## Description

**Chemline ARC-F** is a fast-set, spray applied, two component polyurea that is 100% solids and contains Zero VOCs. It is highlighted by:

- ✓ Excellent corrosion protection and chemical resistance
- ✓ Excellent impact resistance even in sub-freezing weather
- ✓ High abrasion resistance for harsh environments
- ✓ Seamless monolithic waterproof membrane that is tough and durable
- ✓ Odorless, non-toxic vapors

## Application Recommendations

**Chemline ARC-F** adheres extremely well to properly prepared metal, wood, concrete, fiber glass, and other various metal surfaces.

**Chemline ARC-F** must be applied through a two component, high pressure proportioning unit. Material and hoses should be heated to 150°F, with pressure at a minimum of 2200 psi.

Mixing Instructions: Agitate resin blend (B) component thoroughly with a drum mixer before use to disperse pigment and assure homogeneity. Do not thin. Do not agitate in air and moisture.

Consult a Technical Representative regarding specific metal/steel surface preparation and priming requirements. For concrete applications, we recommend **Chemprime 3558** or **Chemprime CP**.

## Packaging, Storage & Shelf Life

**Chemline ARC-F** is available in 5 gallon pails, 55 gallon drums, and 275 gallon totes. It should be stored in sealed containers between 60°F and 90°F. Shelf life is 12 months under normal conditions.

## Safety

**Chemline ARC-F** is for industrial use only. Avoid contact with eyes and skin. Do not inhale or ingest. When spraying, wear a respirator or fresh air hood. Spraying indoors requires forced ventilation. Be sure to read SDS in its entirety prior to use.

## Application Properties

Property	Value
Gel time	5 seconds
Tack free time	20 seconds

## Physical Properties

Property	Value
Hardness, D-2240	D 50
Tensile strength, D-412	3200 psi
100% Modulus, D-412	1500 psi
200% Modulus, D-412	1800 psi
300% Modulus, D-412	2350 psi
Tear strength, DIE-C, D-624	480 pli
Ultimate elongation, D-412	360 %
Abrasion Resistance (CS17 wheels, 1000g, 1000 cycles), D-4060	20 mg loss

\*Values obtained in laboratory setting for comparison purposes only and should not be considered specifications.

Revised 07/2017

Chemline, Inc. • 5151 Natural Bridge Rd. • St. Louis, MO 63115 • Phone: (314) 664 - 2230

• 19500 S. Alameda St. • Los Angeles, CA 90221 • Phone: (310) 764 - 0820

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by Chemline, Inc.



# Chemline ARC-F

**Aromatic Polyurea Coating**

**USGBC LEED, EQ Credit 4:**

**Low-emitting VOC Compliant Materials**

## Surface Preparation

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion. Minimum recommended surface preparation:

**Steel:** Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (3 mils / 75 microns). Prime any bare steel the same day as it is cleaned or before flash rusting occurs, as required.

**Concrete & Masonry:** SSPC-SP13/NACE 6 or ICRI No. 310.2R-2013, CSP 3-5. Surfaces should be thoroughly clean and dry. Concrete and mortar must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, form release agents, moisture curing membranes, loose cement and hardeners. Fill bug holes, air pockets and other voids with recommended repair material.

**Moisture content:** Use calcium chloride test: 3 lb./24 hr./1,000 ft<sup>2</sup>. Concrete shall be 5% maximum as per ASTM F2170 & ASTM F2420. Substrate and air temperature must be 5°F above dew point and rising before material application.

Check for soluble salts on surfaces to be coated. If amount of soluble salts exceeds recommended limits, treat accordingly. Repeat process until acceptable limits are reached. Maximum amounts of soluble salts (micrograms per square centimeter): Chlorides - 3 immersion, 7 non-immersion. Nitrates - 5 immersion, 10 non-immersion. Sulfates - 10 immersion, 20 non-immersion.

If required, holiday test in accordance with ASTM D5162 for steel, or ASTM D4787 for concrete.

*Revised 07/2017*

Chemline, Inc. • 5151 Natural Bridge Rd. • St. Louis, MO 63115 • Phone: (314) 664 - 2230

• 19500 S. Alameda St. • Los Angeles, CA 90221 • Phone: (310) 764 - 0820

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by Chemline, Inc.